11) Publication number:

0 367 629 A1

12	EUROPEAN PATENT APPLICATION										
•	Application number: 89311432.2 Date of filing: 03.11.89	5 1)	Int. Cl. ⁵ C08L 27/18 , H01B 3/44 , H01B 7/36								
43	Priority: 04.11.88 GB 8825860 Date of publication of application: 09.05.90 Bulletin 90/19 Designated Contracting States: AT BE CH DE ES FR GB GR IT LI LU NL SE		Applicant: BICC Public Limited Company Devonshire House Mayfair Place London W1X 5FH(GB) Inventor: Coxon, Eric 34 Gorsey Croft Eccleston Park Prescot Merseyside L34 2RT(GB)								
		74	Representative: Poole, Michael John et al BICC pic Group Patents & Licensing Dept. Network House 1, Ariel Way Wood Lane London W12 7SL(GB)								

- Fluorocarbon polymer compositions and electric cables.
- A polymer composition for high-performance cables or other products requiring laser markings comprises 0.5-15% (preferably 1-10%) of a conjugated aromatic polymer (eg PEEK) dispersed in a fully fluorinated polymer matrix (eg FEP). A good white is attained without pigment, but pigments can be used eg to obtain coloured backgrounds.

EP 0 367 629 A1

FLUOROCARBON POLYMER COMPOSITIONS AND ELECTRIC CABLES

This invention relates to fluorocarbon compositions and to products, more especially but not exclusively electric cables, in which they are used.

Polymers that are completely fluorinated, or nearly so, such as polytetrafluoro ethylene (PTFE), fluorinated ethylene-propylene copolymer (FEP) and the polymer sold under the trade mark "DuPont" as DuPont PFA are valued for high temperature rating, chemical inertness and good electrical properties; but their inert surfaces do not easily accept durable markings with inks or paints and laser printers tend to be ineffectual; in some cases the laser beam may pass through the polymer without absorption, and in others material may be ablated from the surface without any visible mark resulting; certain lasers working in the ultra-violet region do produce marks, but they are pale grey and not clearly visible.

It is an object of the present invention to provide fluorocarbon polymer compositions that accept clearly visible laser printed markings without significant detriment to temperature rating or to physical or electrical properties.

The composition in accordance with the invention comprises 0.5-15% (by weight of total polymer) of a conjugated aromatic polymer dispersed as light-scattering particles in a matrix of a substantially fully fluorinated polymer.

Preferably the content of the aromatic polymer is in the range 1-10% and more especially 1-5%; contents above 10% may lead to reduced toughness, besides being more expensive, while contents below about 1% may have less than ideal contrast. However, the precise content is not at all critical to the appearance of the markings, within the range defined.

Pigments may be present (in conventional amounts) but a good white is easily achieved without any pigments whatsoever and the use of white pigment by itself appears to have no advantages. Other minor additives can be used, if required.

Suitable conjugated aromatic polymers currently available include polyketones, polyetherketones (especially the one sold by Imperial Chemical Industries plc as PEEK), polysulphones, polyethersulphones, polyimides, polyphenylene sulphides, polyetherimides and certain liquid crystal polymers.

Infra-red, visible and ultra-violet lasers are all expected to give good results.

Examples

30

A series of screened 2-core aircraft cables were jacketed with the compositions shown in Table 1 below. In each case the ingredients were dried and tumble-mixed before supply to the hopper of a conventional thermoplastic-fluorocarbon extruder. The cables were marked using a YAG laser operating at 1064 nm with a beam power of about 5 W; in all cases clearly visible black markings were produced.

35

45

40

50

TABLE 1

5	Ingredient Example:	1	2	3	4	5	6
10	Plain clear FEP	9	9	9	9	9	9
15	White pigmented FEP commercial masterbatch			1			
20	Red pigmented FEP commercial masterbatch				1	3	
25	Plain clear PEEK	1		0.5	0.5	1.5	
30	White pigmented PEEK commercial masterbatch		1				
35	Red pigmented PEEK commercial masterbatch						1
40	Colour	White			Pink		
45	Remarks	A				В	С

- ${\tt A} {\tt barely}$ distinguishable in appearance from Examples ${\tt 50} {\tt 2}$ & 3, perhaps even whiter
 - B darker than Example 4, but still clearly legible
- 55 C dark pink, legible but not as easily.

A series of wires were similarly coated with the compositions detailed in Tables 2 and 3. These were marked using a single pulse of radiation from a 248mm krypton fluoride excimer U.V. laser. In all cases markings clearly legible under a hand lens were obtained.

TABLE 2

0	Ingredient Example:	7	8	9	10	11	12	13
5	Plain clear FEP	9.7	9.5	9.3	9.7	9.5	9.3	9.5
o	Polyether Sulphone (ICI grade 4800P)	0.3	0.5	0.7				
5	Polyether Ketone (ICI grade 220G)			·	0.3	0.5	0.7	
2	Polyphenylene Sulphide (Hoechst Celanese							
5	Fortran W205)							0.5
	Colour			W	hite			
0	Remarks							

TABLE 3

	Ingredient Example:	14	15	16	17	18	19	20
<u> </u>	Plain clear FEP	9.9	9.5	9.7	9.5	9.7	9.5	9.3
	Polysulphone (Amoco P1700)	0.1	0.5					
	Polyetherimide (GE Plastics Ultem)			0.3	0.5	:		
	Liquid Crystal Polymer							
	(ICI Victrex SRP)					0.3	0.5	0.7
	Colour			wi			 -	
	Remarks	D	G		E			F G

- D Slightly translucent, but still clearly legible.
 - E Slightly paler mark than Example 16.
 - F Slightly paler mark than Example 19.
 - G These samples tended to split or crack: a lower content of the aromatic polymer is recommended.

Claims

55

1. A polymer composition comprising 0.5-15% (by weight of total polymer) of a conjugated aromatic

polymer dispersed as light-scattering particles in a matrix of a substantially fully fluorinated polymer.

2 A white polymer composition in accordance with claim 1 and containing no pigment.

15

20

25

30

35

40

45

50

55

- 3. A polymer composition as claimed in claim 1 or claim 2 in which the content of the said aromatic polymer is 1-10%.
- 4. A polymer composition as claimed in claim 1 or claim 2 in which the content of the said aromatic polymer is 1-5%.
- 5. An electic cable with at least one component formed of the composition claimed in any one of claims 1-4.
- 6. Any article having a surface made of the composition claimed in any one of claims 1-4 and having laser-formed markings on that surface.

6



EUROPEAN SEARCH REPORT

EP 89 31 1432

Category	Citation of document with indication of relevant passages	n, where appropriate,	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)				
X	EP-A-O 199 991 (SHANGHA ORGANIC CHEMISTRY ACADEM * Claim 1; examples 7,11	MIA SINICA)	1-4	C 08 L 27/18 H 01 B 3/44 H 01 B 7/36				
X	PATENT ABSTRACTS OF JAPA 185 (C-357)[2241], 27th JP-A-61 31 448 (TORAY IN 13-02-1986	June 1986; &	1-3					
X	PATENT ABSTRACTS OF JAPA 365 (C-532)[3212], 29th & JP-A-63 118 357 (YOBEA K.K.) 23-05-1988	September 1988;	1-3					
				TECHNICAL FIELDS SEARCHED (Int. Cl.5)				
				C 08 L H 01 B				
		•						
,	The present search report has been drav	wn un for all claims						
	Place of search	Date of completion of the search		Examiner				
THE	E HAGUE	09-02-1990	HOFF	MANN K.W.				
X: par Y: par doc	CATEGORY OF CITED DOCUMENTS ticularly relevant if taken alone ticularly relevant if combined with another ument of the same category	T: theory or principl E: earlier patent doc after the filing da D: document cited in L: document cited fo	ument, but publiste n the application or other reasons	ished on, or				
A: technological background O: non-written disclosure P: intermediate document		& : member of the sa	&: member of the same patent family, corresponding document					